



S25068 PLASTER 2000 LD

					
1000 ml 1000 ml	Knifing application	5-6 h at 20°C	0-2 Cm	24h at 20°C	P 80 P 120

Description

Filler

2K epoxy filler with light extender. Used in the yachting field to level surfaces.
Low shrinking product with good elasticity, especially suitable for fibreglass boats.

Colour

The base is light yellow, the hardener is light blue,

Characteristics

- Low specific weight
- Good workability
- Very good flexibility

Specific weight A and B $0,50 \pm 0,05$ g/ml
Shore D hardness: 35

Substrate preparation

Stoppani epoxy primers

Dry sanding with P 280-320 paper

Application

Knifing.

Mixing ratio

		Volume	Weight
S25068	PLASTER 2000 LD	1000 ml	1000 g
S25069	PLASTER 2000 LD HARDENER	1000 ml	1000 g

Pot-life at 20°C: 1 h

N° of knifing: 1+1 of refinish

Recommended film thickness : no more than 2cm each coat

Theoretical coverage A+ B: 0,2 m² for 1lt mixture at 5 mm dry film thickness

Rises in temperature cause pot-life reduction

Drying

	10°C	20°C	35°C
Sanding after	min.48 h	min. 24 h	min. 12 h

TECHNICAL DATA SHEET N° S133-GB
UPDATED 08/2011

All information here included is the result of carefully controlled tests and expresses our best and up to date knowledge. This news is given only as an information, so the firm cannot be accountable for further results. Furthermore it cannot be used as a contestation related to the use of the described product. All this is due to the fact that use conditions are not under our control.



Lechler S.p.A. 22100
COMO ITALY - Via Cecilio, 17
Tel. +39.031 586 111 - Fax +39.031 586 206
info@lechler.eu www.lechler.eu